



SPECIFICATION OF BITUMEN AH-70			
Penetration	1/10 Millimetres (mm)	60-70	ASTM D5
Density, 25°C	Kilogram per Cubic Meter (kg/m ³)	1.000/1.060	ASTM D71/D328
Loss On Heating	Weight Percentage (WT%)	0.2 Max	ASTM D6
Flash Point (Cleveland Open Cup)	Flash Point (Cleveland Open Cup)	250 min	ASTM D92
Spot Test	Negative (–) or Positive (+)	Negative	AASHOT 102 *